

75 AMP. RATING

Expressed in minutes; the amount of time it takes a battery to go from fully charged to 1.75 volts per cell using a constant 75 amp discharge at 80°F.

20 HOUR RATE

Expressed in Ampere Hours; the total amount of Ampere Hours a fully charged battery can provide in a 20 hour period, reaching a discharge level of 1.75 volts per cell at 80°F. Divide the rating by 20 (hrs) to determine discharge current rate.

6 HOUR RATE

Expressed in Ampere Hours; the total amount of Ampere Hours a fully charged battery can provide in a 6 hour period, reaching a discharge level of 1.75 volts per cell at 80°F. Divide the rating by 6 (hrs) to determine discharge current rate.

CONVERT 20 HR. TO 6 HR CAPACITY

Multiply 20 Hr. Ampere Hour Capacity by .84 (Divide result by 6 to determine discharge current rate).

RESERVE CAPACITY

Expressed in minutes, the time it takes for a fully charged battery to reach 1.75 volts per cell using a constant 25 amp. discharge at 80°F.

C.C.A. (Cold Cranking Amps)

Expressed in amps., a rating usually applied to S.L.I. (starting, lighting, ignition) batteries; the highest discharge amps, that can be sustained by a fully charged battery over 30 seconds without dropping voltage below 1.2 volts per cell at 0°F.

C.A. / M.C.A. (Cranking Amps)

Same as above except that the rating is at 32°F rather than 0°F. The higher temperature will result in an approximate increase in the cranking rate of 22%.

Founded in 1926, U.S. Battery Manufacturing Company has established a long history in the manufacture and development of premium grade, deep cycle batteries. Originally, the product line was limited to heavy-duty batteries, many of which were specially designed to serve the fishing industry. As U.S. Battery grew, so did its product line; building a tradition of quality and durability. Today U.S. Battery is recognized as a leading manufacturer of Deep Cycle batteries specializing in golf car, sweeper /scrubber, aerial lifts, marine and special application types. U.S. Battery also produces a complete line of Low Maintenance commercial, farm, marine, military and special purpose starting batteries. The company has three large, modern plants; the corporate headquarters located in Corona, California with a second manufacturing facility in Evans, Georgia and the newest facility in Augusta Georgia. U.S. distributes its products domestically as well as having a strong international market base.



U.S. BATTERY MFG., INC.
1675 Sampson Ave., Corona, CA 92879
(951) 371-8090 • (800) 695-0945
FAX (951) 371-4671



U.S. BATTERY MFG., INC.
1895 Tobacco Road, Augusta, GA 30906
(800) 522-0945 • Fax: (706) 772-7756

www.usbattery.com

Go To The XTREME
www.usbattery.com



DEEP CYCLE BATTERY CARE AND MAINTANCE

PROPER CARE AND MAINTENANCE OF DEEP CYCLE BATTERIES

XB New batteries should be given a full charge before use.

XB New deep cycle batteries need to be cycled several times before reaching full capacity (50 - 125 cycles, depending on type). Capacity will be limited during this period.

XB Battery cables should be intact, and the connectors kept tight at all times. Always use insulated tools to avoid shorting battery terminals. Regular inspection is recommended.

XB Vent caps should be correctly installed and tight during vehicle operation and battery charging.

XB Batteries should be kept clean and free of dirt and corrosion at all times.

XB Batteries should always be watered after charging unless plates are exposed before charging. If exposed, plates should be covered by approximately 1/8" of acid. Check acid level after charge. The acid level should be kept 1/4" below the bottom of the fill well in the cell cover.

XB Water used to replenish batteries should be distilled or treated not to exceed 200 T.D.S. (total dissolved solids...parts per million). Particular care should be taken to avoid metallic contamination (iron).

XB For best battery life, batteries should not be discharged below 80% of their rated capacity. Proper battery sizing will help avoid excessive discharge.

XB Battery chargers should be matched to fully charge batteries in an eight hour period. Defective and unmatched chargers will damage batteries or severely reduce their performance.

XB Avoid charging at temperatures above 120°F or ambient, whichever is higher.

XB Deep cycle batteries need to be equalized periodically. Equalizing is an extended, low current charge performed after the normal charge cycle. This extra charge helps keep all cells in balance. Actively used batteries should be equalized once per month. Manually timed charger should have the charge time extended approximately 3 hours. Automatically controlled charger should be unplugged and reconnected after completing a charge.

XB In situations where multiple batteries are connected in series, parallel or series/parallel, replacement battery(s) should be of the same size, age and usage level as the companion batteries. Do not put a new battery into a pack which has 50 or more cycles. Either replace with all new or use a good used battery(s).

XB Periodic battery testing is an important preventative maintenance procedure. Hydrometer readings of each cell (fully charged) gives an indication of balance and true charge level. Imbalance could mean the need for equalizing; is often a sign of improper charging or a bad cell. Voltage checks (open circuit, charged and discharged) can locate a bad battery or weak battery. Load testing will pick out a bad battery when other methods fail. A weak battery will cause premature failure of companion batteries.

XB Always use a matched charger and battery pack system. Unmatched chargers will cause potential problems.

XB As batteries age, their maintenance requirements change. This means longer charging time and/or higher finish rate (higher amperage at the end of the charge). Usually older batteries need to be watered more often. And, their capacity decreases.

XB Lead acid batteries should be brought up to full charge at the earliest opportunity. Avoid continuously operating batteries in a partially charged condition. This will shorten their life and reduce their capacity.

XB Extreme temperatures can substantially affect battery performance and charging. Cold reduces battery capacity and retards charging. Heat increases water usage and can result in overcharging. Very high temperatures can cause "thermal run-away" which may lead to an explosion or fire. If extreme temperature is an unavoidable part of an application, consult a battery/charger specialist about ways to deal with the problem.

XB Inactivity can be extremely harmful to all lead acid batteries. If seasonal use is anticipated, we recommend the following:

- A.) Completely charge the battery before storing.
- B.) Remove all electrical connections from the battery, including series/parallel connectors.
- C.) Store the battery in as cool a place as possible. However, do not store in a location which will consistently be below 32°F. Batteries will discharge when stored, the lower the temperature the lower the self discharge.
- D.) When not in use, boost every two months.



DEEP CYCLE BATTERY APPLICATIONS

Golf Cars • Floor Sweepers • Floor Scrubbers • Aerial Lifts • R.V.s • Electric Cars
UPS Systems • Personnel Carriers • Pallet Jacks • Towing Tractors • Electric Boats
Photovoltaic Systems • Yachts • Trolling Motors

www.usbattery.com